

# Exact Products, Inc.

## Technical Data Sheet

Exact brand PVC Fence

TEST Method	DESCRIPTION	TEST RESULTS	ALLOWED
AAS	Lead PPM	Not Detected	Not Detected
AAS	TIO2 % & PPH (Dupont 105)	10% & 11 PPH	
ASTM F964-02	Height	+1/32"	+1/16"
	Width	+1/32"	+1/16"
	Weight Tolerance	<10%	<10%
	Impact Resistance (ft lbf/mil)		
	@32F	>0.75	>0.75
	@74F	>1.50	>1.50
	Warp	0.18%	<0.5%
	Coff. of Linear Expansion	2.3	<4.4
	Dimensional Stability	1.5%	<2.4%
ASTM D 792	Specific Gravity	1.46 g/ml	
ASTM D 2240	Hardness Shore D	82	
ASTM D 648	Heat Deflection-(264 psi)	155.6F	
ASTM G155	Xenon Arc Accelerated Weathering 2000 Hrs	1.3 ΔE (for White)	



Marketed by Summit Building Products; 602-363-7619 or 970-669-6477  
Produced & Distributed by Exact Products, Inc.